Renotex

D 4000 S

UNIVERSAL ADHESIVE FOR FLOOR COVERINGS



PRODUCT INFORMATION PAGE

TECHNICAL DATA:

Nr. art. 0998

BASE:	Polymer dispersion
COLOUR:	Ash gray
DENSITY:	approx. 1,1 g/cm^3
APPLICATION TEMPERATURE:	minimum 15°C
PRE-EVAPORATION TIME:	10-40 minutes
OPEN TIME:	approx. 50 min
LOAD RESISTANCE:	after 24 hours
SEAM WELDING:	after 24 hours
FINAL STRENGTH:	after approx. 72 hours
CLEANING:	uncured adhesive – water; cured adhesive – acetone
CONSUMPTION:	200-400 g/m^2 depending on the type of material being bonded and the bonding method
PACKAGING:	12kg bucket

PROPERTIES:
A universal adhesive based on polymer dispersions, with a long open time and wide range of applications. Safe for health. Fire-resistant. Moisture-resistant. Easy to apply and recommended where high bonding strength is required for the adhered surfaces.

APPLICATION:
For use on absorbent substrates. Suitable for bonding PVC surfaces (both soft and hard), vinyl tiles (LVT), and linoleum. Can be used on underfloor heating systems.

SUBSTRATE PREPARATION:
The surfaces to be bonded must be clean, free from dust, grease, and other contaminants. The substrate should be even and dry.

USAGE INSTRUCTIONS:
Before starting the work, thoroughly mix the adhesive. Apply only as much adhesive as can be covered with the floor covering within the open time. For deformed floor coverings, they should be weighted down.

Wet/ Semi-wet application: Apply adhesive to one of the bonding surfaces, join them together, and press them across the entire contact area. The surfaces should be joined while the adhesive is still wet, but no later than 50 minutes after application. Apply the adhesive with a trowel of appropriate notch size, a roller, or a brush. Drying time depends on the amount of adhesive applied, pressure, and temperature.

Note: The adhesive does not provide good adhesion or has limited adhesion before the initial evaporation.

STORAGE:
12 months at a temperature at 10°C to 20°C. Protect from frost.

The mixture has not been classified as hazardous according to the criteria of Regulation (EC) No. 1272/2008.

For difficult problem-solving questions, or products with special requirements, which are not covered by this technical card, we assure all our clients of our professional consulting services. Upon issue of a new technical card, the present one will no longer be valid.