Renove

Renovacol

PU-112 R

THINNER MIXTURE



PRODUCT INFORMATION PAGE

TECHNICAL DATA:

Nr. art. 0955

FORM:	liquid
COLOUR:	transparent light brown
ODOUR:	weak
SOLUBILITY:	thinner
DRYING TIME:	1,5 to 2 hours
STEPPING ON ALLOWED:	after 2-3 hours
FORD VISCOSITY CUP:	4 mm/(ISO2431) ca. 15 seconds
SUITABLE FOR USE:	24 months from production date
PACKAGE:	5L

PROPERTIES:
Thinner mixture for the polyurethane primer Renoprimer PU-112.

APPLICATION:
For use before adherence of parquets with URETAX - 2k on absorptive and non-absorptive grounds with increased residual moisture.

METHOD OF USE:
Apply on dry surfaces free from contamination, traces of moisture. Apply evenly using a roller or brush. The first layer must be applied using thinner RENOVACOL PU-112R, adding 20% to 40%. The second layer must be applied after 10 hours. Adherence of parquet can be commenced after 5-7 hours from priming. In order to improve adherence of the ground to the glue, the last wet layer of the ground must be covered with quartz sand (from 0.3 to 1 mm).

CONSUMPTION:
Concrete ground priming from 0.2 - 0.5 l/m^2.

STORAGE:
Store in the originally sealed packaging, in a dry place, in temperature at 5°C to 25°C.

INSTRUCTIONS:
In case of long-term storage, mix the preparation before use.

For difficult problem-solving questions, or products with special requirements, which are not covered by this technical card, we assure all our clients of our professional consulting services. Upon issue of a new technical card, the present one will no longer be valid.